



Phone No.: 9980273779 Email: varadindustries2021@gmail.com
GSTIN: 29AAUFV2701P1ZC State: 29-Karnataka

Sodium Based Bentonite Powder

Specification	
Elements	Range
Moisture Content	12 % Min
Dry Fineness (passing from 200 mesh)	85 % Min
pH Value (5% suspension)	9 Min
Free Swelling Capacity	30 ML Min
Gelling time (10% suspension)	45 Sec Max
Green Compression Strength	850 Gm/cm ² Min
Wet Tensile Strength	30 Gm/cm ² Min
Methylene Blue Requirement	390 Mg/g Min